

Polishing Alumina

AC34

Standard Calcined Alumina

PRODUCT INFORMATION

Hard calcined aluminium oxide Al₂O₃, mainly alpha phase, with a medium soda content.

This grade is used for the production of ceramics, electrofused bricks, fibers, corundum and in the polishing industry.

CHARACTERISTICS

Physical Characteristics	Unit	Typical Value
Particle Size Distribution (Malvern)		
D50	µm	70
< 15 µm	%	13
< 125 µm	%	88
Blaine Surface Area	cm ² /g	5300
Bulk Density	g/cm ³	0.85
Loss on ignition 20°C/1000°C	%	0.13
Chemical Characteristics	Unit	Typical Value
Al ₂ O ₃ (by difference)	%	99.6
Na ₂ O total	ppm	3600
CaO	ppm	130
SiO ₂	ppm	130
Fe ₂ O ₃	ppm	130
Polishing Characteristics	Unit	Typical Value
Oleic Acid absorption	ml/100g	52
Cut		8
Polish		2

Valid after : 2005/10/14

C.A.S. : 1344-28-1



For Information Only

CHEMIA BRUGG



Chemia Brugg AG Telefon +41 (056) 460 62 60
 GB Chemie Telefax +41 (056) 441 45 62
 Aarauerstrasse 51 Web www.chemia.ch
 CH-5200 Brugg e-Mail chemie@chemia.ch